

Qualification & Reliability Report

DDR4 SDRAM 16Gb, 32Gb

16Gb,x8: 78b TFBGA
AS4C2G8D4A-62BCN

16Gb, x16: 96b TFBGA
AS4C1G16D4A-62BCN

32Gb,x8: 78b TFBGA
AS4C4G8D4-62BCN

32Gb, x16: 96b TFBGA
AS4C2G16D4-62BCN

IMPORTANT NOTICE

ALLIANCE MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, AS TO THE RELIABILITY TEST RESULTS/FAILURE RATE ESTIMATES CONTAINED HEREIN, EXCEPT THAT ALLIANCE WARRANTS THAT IT PERFORMED THE RELIABILITY TESTS DESCRIBED HEREIN ACCORDING TO THE SPECIFIED STANDARDS AND THAT THIS REPORT ACCURATELY REFLECTS THE RESULTS OF SUCH TESTS. CUSTOMER EXPRESSLY ACKNOWLEDGES THAT THESE RELIABILITY TEST RESULTS/ FAILURE RATE ESTIMATES ARE ONLY VALID FOR MECHANISMS KNOWN TO BE TEMPERATURE AND/OR VOLTAGE DEPENDENT AND THAT SUCH RELIABILITY TEST RESULTS/ FAILURE RATE ESTIMATES ARE SUBJECT TO OTHER SIGNIFICANT INHERENT LIMITATIONS, INCLUDING BUT NOT LIMITED TO LOW FAILURE COUNTS, TESTING CONDITIONS, ASSUMPTIONS AS TO TYPICAL OPERATING CONDITIONS AND ACCELERATION FACTORS AND LOT-TO-LOT VARIABILITY. CUSTOMER FURTHER ACKNOWLEDGES THAT THESE TESTS WERE CONDUCTED IN SEMICONDUCTOR TEST EQUIPMENT AND NOT IN AN ACTUAL CUSTOMER APPLICATION. THE ACTUAL RELIABILITY RESULTS/FAILURE RATES IN AN ACTUAL APPLICATION MAY MATERIALLY DIFFER DUE TO THE SPECIFIC OPERATING CONDITIONS (INCLUDING BUT NOT LIMITED TO TEMPERATURE AND VOLTAGE), HANDLING AND STORAGE OF THE PRODUCTS, INSTALLATION PROCEDURES, AND THE ACTUAL ENVIRONMENTAL AND ELECTRICAL CONDITIONS THE PRODUCT IS SUBJECT TO IN THE APPLICATION. TO DETERMINE PRODUCT RELIABILITY/FAILURE RATES IN A SPECIFIC APPLICATION, RELIABILITY TESTING MUST BE PERFORMED IN SUCH APPLICATION AS PART OF THE INTERNAL QUALIFICATION OF THE PRODUCT.

MICRON'S PRODUCTS ARE NOT AUTHORIZED FOR USE IN LIFE SUPPORT DEVICES OR CRITICAL APPLICATIONS WITHOUT THE EXPRESS WRITTEN APPROVAL OF THE GLOBAL QUALITY VICE PRESIDENT OR BUSINESS UNIT VICE PRESIDENT OF ALLIANCE. CRITICAL APPLICATIONS ARE THOSE APPLICATIONS IN WHICH FAILURE OF THE ALLIANCE COMPONENT COULD RESULT, DIRECTLY OR INDIRECTLY, IN DEATH, PERSONAL INJURY OR SEVERE PROPERTY OR ENVIRONMENTAL DAMAGE.

EXCEPT AS EXPRESSLY PROVIDED IN A BINDING AGREEMENT SIGNED BY ITS DULY AUTHORIZED REPRESENTATIVE, ALLIANCE MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF NONINFRINGEMENT, ANY WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. NO AGENT, EMPLOYEE OR REPRESENTATIVE OF ALLIANCE HAS ANY AUTHORITY TO BIND ALLIANCE TO ANY AFFIRMATION, REPRESENTATION OR WARRANTY RELATING TO THE PRODUCTS OTHER THAN AS SPECIFICALLY PROVIDED HEREIN AND CUSTOMER ACKNOWLEDGES AND AGREES THAT ANY SUCH PURPORTED WARRANTY, AFFIRMATION OR REPRESENTATION SHALL BE VOID AND OF NO FORCE AND EFFECT.

AUTOMOTIVE APPLICATIONS: PRODUCTS ARE NOT DESIGNED OR INTENDED FOR USE IN AUTOMOTIVE APPLICATIONS UNLESS SPECIFICALLY DESIGNATED BY ALLIANCE AS AUTOMOTIVE-GRADE BY THEIR RESPECTIVE DATA SHEETS. DISTRIBUTOR AND CUSTOMER/DISTRIBUTOR SHALL ASSUME THE SOLE RISK AND LIABILITY FOR AND SHALL INDEMNIFY AND HOLD ALLIANCE HARMLESS AGAINST ALL CLAIMS, COSTS, DAMAGES, AND EXPENSES AND REASONABLE ATTORNEYS' FEES ARISING OUT OF, DIRECTLY OR INDIRECTLY, ANY CLAIM OF PRODUCT LIABILITY, PERSONAL INJURY, DEATH, OR PROPERTY DAMAGE RESULTING DIRECTLY OR INDIRECTLY FROM ANY USE OF NON-AUTOMOTIVE-GRADE PRODUCTS IN AUTOMOTIVE APPLICATIONS. CUSTOMER/DISTRIBUTOR SHALL ENSURE THAT THE TERMS AND CONDITIONS OF SALE BETWEEN CUSTOMER/DISTRIBUTOR AND ANY CUSTOMER OF DISTRIBUTOR/CUSTOMER (1) STATE THAT ALLIANCE PRODUCTS ARE NOT DESIGNED OR INTENDED FOR USE IN AUTOMOTIVE APPLICATIONS UNLESS SPECIFICALLY DESIGNATED BY ALLIANCE AS AUTOMOTIVE-GRADE BY THEIR RESPECTIVE DATA SHEETS AND (2) REQUIRE SUCH CUSTOMER OF DISTRIBUTOR/CUSTOMER TO INDEMNIFY AND HOLD ALLIANCE HARMLESS AGAINST ALL CLAIMS, COSTS, DAMAGES, AND EXPENSES AND REASONABLE ATTORNEYS' FEES ARISING OUT OF, DIRECTLY OR INDIRECTLY, ANY CLAIM OF PRODUCT LIABILITY, PERSONAL INJURY, DEATH, OR PROPERTY DAMAGE RESULTING DIRECTLY OR INDIRECTLY FROM ANY USE OF NON-AUTOMOTIVE-GRADE PRODUCTS IN AUTOMOTIVE APPLICATIONS.



Table of Contents

Table 1: 1a nm — Die Quals 4

Table 2: Package: 16Gb SDP-78b TFBGA5

Table 3: Package: 16Gb SDP-96b TFBGA.....6

Table 4: Package: 32Gb DDP-78b TFBGA7

Table 5: Package: 32Gb DDP-96b TFBGA8

Qualification Result

Qualification Results — 16Gb DDR4 SDRAM

Table 1: 1α nm — Fabrication

	Test Procedure / Conditions	Test Method Referenced	Duration or Level	Results		Notes
				# Lots	Failed / Tested	
Reliability Level Tests	HIGH TEMPERATURE OPERATING LIFE <i>Stress Conditions:</i> 125°C, 1.3V internal voltage <i>Typical Operating Conditions:</i> 50°C, 1.0V internal voltage at 1.2V external Vdd; 16 FITs Ea=0.5eV; β=7; AFOVERALL=241; Pn=0.916; Device Hrs=2.328 x 10 ⁵	JESD22-A108	168 hrs 504 hrs 1008 hrs	3	0 / 231 0 / 231 0 / 231	1,2
	EARLY LIFE FAILURE RATE <i>Stress Conditions:</i> 125°C, 1.3V internal voltage <i>Typical Operating Conditions:</i> 50°C, 1.0V internal voltage at 1.2V external Vdd; 21 FITs Ea=0.5eV; β=7; AFOVERALL=241; Pn=0.916; Device Hrs=1.8 x 10 ⁵	JESD22-A108	36 hrs	3	0 / 5000	1,2
	LOW TEMPERATURE OPERATING LIFE -10°C, 1.3V internal voltage	JESD22-A108	168 hrs 504 hrs 1008 hrs	3	0 / 231 0 / 231 0 / 231	1,2
	HIGH TEMPERATURE STORAGE LIFE 150°C, no bias.	JESD22-A103	504 hrs 1008 hrs	3	0 / 231 0 / 231	1,2
Characterization Tests	ELECTROSTATIC DISCHARGE Human Body Model Charged Device Model	JS-001 JS-002	2,000V 500V	3 3	0 / 3 0 / 3	1
	LATCH-UP (105°C) ITrigger	JESD78	100mA	3	0 / 6	1
	Overvoltage VSUPPLY		VDD/VDDQ = 1.9V VPP = 4.2V	3	0 / 6	
Wafer Level Tests	TIME DEPENDENT DIELECTRIC BREAKDOWN (TDDB)	JESD35A, JESD35-2, JESD92	>10 years	3	Pass	
	ELECTROMIGRATION (EM)	JESD63, JESD61A, JESD202A, JESD87	>10 years	3	Pass	
	CHANNEL HOT CARRIER (CHC)	JESD28, JESD60A	>10 years	3	Pass	
	NEGATIVE BIAS TEMPERATURE INSTABILITY (NBTI)	JESD90	>10 years	3	Pass	

- (1) Alliance primarily references JEDEC standard JESD47 when conducting reliability tests for the qualification of new product. In some tests, other industry standards may be referenced. Note that many tests are carried beyond the minimum recommended by JEDEC. This is to verify that margin exists with respect to intrinsic reliability.
- (2) Preconditioning (without soak): per JEDEC J-STD-020D. Test is performed with 260°C peak reflow.

Qualification Results — 16Gb DDR4 SDRAM (continued)

Table 2: Package: SDP-78b TFBGA

	Test Procedure / Conditions	Test Method Referenced	Duration or Level	Results		Notes
				# Lots	Failed / Tested	
Reliability Level Tests	HIGHLY ACCELERATED STRESS TEST 110°C, 85% RH, 1.26V on alternating balls.	JESD22-A110	264 hrs	3	0 / 231	1,2
	TEMPERATURE CYCLE -55°C for 15 min., + 125°C for 15 min., air to air.	JESD22-A104	250 cycles 500 cycles 1000 cycles	3	0 / 231 0 / 231 0 / 231	1,2
	HIGH TEMPERATURE STORAGE LIFE 150°C, no bias.	JESD22-A103	504 hrs 1008 hrs	3	0 / 231	1,3
Characterization Tests	MOISTURE SENSITIVITY LEVEL Peak Reflow Temp = 260°C	J-STD-020	minimum Level 3	3	Pass	1
	SOLDERABILITY 245°C peak reflow temperature, FR4 substrate, ROL0 SnAgCu solder paste.	J-STD-002D		3	0 / 15	1
	BOND INTEGRITY Wire Bond Shear minimum gmf Wire Bond Pull Strength minimum gmf	JESD22-B116 Internal Alliance specs		3 3	14.11 gmf 2.87 gmf	1
	SOLDER BALL SHEAR 240°C peak reflow temperature, 1x reflow, minimum gmf	JESD22-B117		3	776.23 gmf	1

- (1) Alliance primarily references JEDEC standard JESD47 when conducting reliability tests for the qualification of new product. In some tests, other industry standards may be referenced. Note that many tests are carried beyond the minimum recommended by JEDEC. This is to verify that margin exists with respect to intrinsic reliability.
- (2) Preconditioning (with soak): per JEDEC J-STD-020D at rated moisture sensitivity level. Test is performed with 260°C peak reflow.
- (3) Preconditioning (without soak): per JEDEC J-STD-020D. Test is performed with 260°C peak reflow.
- (4) Data leveraged from similar package.

Qualification Results — 16Gb DDR4 SDRAM (continued)

Table 3: Package: SDP-96b TFBGA

	Test Procedure / Conditions	Test Method Referenced	Duration or Level	Results		Notes
				# Lots	Failed / Tested	
Reliability Level Tests	HIGHLY ACCELERATED STRESS TEST 110°C, 85% RH, 1.26V on alternating balls.	JESD22-A110	264 hrs	3	0 / 231	1,2
	TEMPERATURE CYCLE -55°C for 15 min., + 125°C for 15 min., air to air.	JESD22-A104	500 cycles 750 cycles 1000 cycles	3	0 / 231	1,2
	HIGH TEMPERATURE STORAGE LIFE 150°C, no bias.	JESD22-A103	504 hrs 1008 hrs	3	0 / 231	1,3
Characterization Tests	MOISTURE SENSITIVITY LEVEL Peak Reflow Temp = 260°C	J-STD-020	minimum Level 3	3	Pass	1
	SOLDERABILITY 245°C peak reflow temperature, FR4 substrate, ROL0 SnAgCu solder paste.	J-STD-002D		3	0 / 15	1,4
	BOND INTEGRITY Wire Bond Shear minimum gmf Wire Bond Pull Strength minimum gmf	JESD22-B116 Internal Alliance specs		3 3	10.40 gmf 3.39 gmf	1
	SOLDER BALL SHEAR 240°C peak reflow temperature, 1x reflow, minimum gmf	JESD22-B117		3	747.69 gmf	1

- (1) Alliance primarily references JEDEC standard JESD47 when conducting reliability tests for the qualification of new product. In some tests, other industry standards may be referenced. Note that many tests are carried beyond the minimum recommended by JEDEC. This is to verify that margin exists with respect to intrinsic reliability.
- (2) Preconditioning (with soak): per JEDEC J-STD-020D at rated moisture sensitivity level. Test is performed with 260°C peak reflow.
- (3) Preconditioning (without soak): per JEDEC J-STD-020D. Test is performed with 260°C peak reflow.
- (4) Data leveraged from similar package.

Qualification Results — 32Gb DDR4 SDRAM (continued)

Table 4: Package: DDP-78b TFBGA

	Test Procedure / Conditions	Test Method Referenced	Duration or Level	Results		Notes
				# Lots	Failed / Tested	
Reliability Level Tests	HIGHLY ACCELERATED STRESS TEST 110°C, 85% RH, 1.26V on alternating balls.	JESD22-A110	264 hrs	3	0 / 231	1,2
	TEMPERATURE CYCLE -55°C for 15 min., + 125°C for 15 min., air to air.	JESD22-A104	250 cycles 500 cycles 1000 cycles	3	0 / 231 0 / 231 0 / 231	1,2
	HIGH TEMPERATURE STORAGE LIFE 150°C, no bias.	JESD22-A103	504 hrs 1008 hrs	3	0 / 231 0 / 231	1,3
Characterization Tests	MOISTURE SENSITIVITY LEVEL Peak Reflow Temp = 260°C	J-STD-020	minimum Level 3	3	Pass	1
	SOLDERABILITY 245°C peak reflow temperature, FR4 substrate, ROL0 SnAgCu solder paste.	J-STD-002D		3	0 / 15	1
	BOND INTEGRITY Wire Bond Shear minimum gmf Wire Bond Pull Strength minimum gmf	JESD22-B116 Internal Alliance specs		3 3	9.31 gmf 3.63 gmf	1
	SOLDER BALL SHEAR 240°C peak reflow temperature, 1x reflow, minimum gmf	JESD22-B117		3	1083.04 gmf	1

- (1) Alliance primarily references JEDEC standard JESD47 when conducting reliability tests for the qualification of new product. In some tests, other industry standards may be referenced. Note that many tests are carried beyond the minimum recommended by JEDEC. This is to verify that margin exists with respect to intrinsic reliability.
- (2) Preconditioning (with soak): per JEDEC J-STD-020D at rated moisture sensitivity level. Test is performed with 260°C peak reflow.
- (3) Preconditioning (without soak): per JEDEC J-STD-020D. Test is performed with 260°C peak reflow.
- (4) Data leveraged from similar package.

Qualification Results — 32Gb DDR4 SDRAM

Table 5: Package: DDP-96b TFBGA

	Test Procedure / Conditions	Test Method Referenced	Duration or Level	Results		Notes
				# Lots	Failed / Tested	
Reliability Level Tests	HIGHLY ACCELERATED STRESS TEST 110°C, 85% RH, 1.26V on alternating balls.	JESD22-A110	264 hrs	3	0 / 231	1,2
	TEMPERATURE CYCLE -55°C for 15 min., + 125°C for 15 min., air to air.	JESD22-A104	250 cycles 500 cycles 1000 cycles	3	0 / 231 0 / 231 0 / 231	1,2
	HIGH TEMPERATURE STORAGE LIFE 150°C, no bias.	JESD22-A103	504 hrs 1008 hrs	3	0 / 231 0 / 231	1,3
Characterization Tests	MOISTURE SENSITIVITY LEVEL Peak Reflow Temp = 260°C	J-STD-020	minimum Level 3	3	Pass	1
	SOLDERABILITY 245°C peak reflow temperature, FR4 substrate, ROL0 SnAgCu solder paste.	J-STD-002D		3	0 / 15	1
	BOND INTEGRITY Wire Bond Shear minimum gmf Wire Bond Pull Strength minimum gmf	JESD22-B116 Internal Alliance specs		3 3	10.53 gmf 5.20 gmf	1
	SOLDER BALL SHEAR 240°C peak reflow temperature, 1x reflow, minimum gmf	JESD22-B117		3	1081.50 gmf	1

- (1) Alliance primarily references JEDEC standard JESD47 when conducting reliability tests for the qualification of new product. In some tests, other industry standards may be referenced. Note that many tests are carried beyond the minimum recommended by JEDEC. This is to verify that margin exists with respect to intrinsic reliability.
- (2) Preconditioning (with soak): per JEDEC J-STD-020D at rated moisture sensitivity level. Test is performed with 260°C peak reflow.
- (3) Preconditioning (without soak): per JEDEC J-STD-020D. Test is performed with 260°C peak reflow.
- (4) Data leveraged from similar package.